



PERGOPAK[®] M4

Einsatzbeispiele / Applications

PERGOPAK wird als Lackhilfsmittel mit mattierenden Eigenschaften in der Lackindustrie eingesetzt.

Die Hauptvorteile sind: • intensive Mattierungswirkung • geringe Rheologiebeeinflussung • Verbesserung der Kratzfestigkeit • Elastizität, Adhäsion, Witterungs-, Temperatur- und Glanzstabilität.

PERGOPAK is used as a matting and effects agent for the paint and varnish industry. Its main advantages are: • high matting efficiency • low impact on rheology • improved scratch and abrasion resistance • improvement of adhesion and elasticity • excellent weather resistance and gloss retention

Durchschnittsanalyse / Typical analysis

Chemische Konstitution / Chemical composition

| | | |
|--|---|----------------------------|
| Polymethylharnstoffharz mit freien Methylolgruppen | [%] | ca. 0.6 |
| Polymethyl urea resin with reactive methylol groups | [%] | approx. 0.6 |
| Dichte / Density | [g/cm ³] | 1.47 |
| Schüttdichte / Bulk density | [kg/m ³] | ca. 80 |
| Spez. Verpackungsgewicht (gepresst) / Packed bulk density (compressed) | [kg/m ³] | ca. 200 |
| Teilchengröße (Laser Beugung) / Particle Size (laser diffraction) | d ₅₀ [µm] d ₉₀ [µm] d ₁₀₀ [µm] | 5 – 7 12 – 15.5 ≤ 30 |
| Spezifische Oberfläche (BET) / Specific surface (BET) | [m ² /g] | 14 – 22 |
| Ölaufnahme / Oil absorption | [cm ³ /100g] | ca. 310 |
| Brechungsindex / Refractive index | | 1.607 |
| Feststoff-Gehalt / Solid content | [%] | ≥ 83 |
| Zersetzungstemperatur / Decomposition temperature | [°C] | > 220 |
| Lagerstabilität / Storage stability | Jahre / years | > 1 |

Shipping Information

Transportation classification: not regulated for transportation
Harmonized tariff number: 39091000

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

| | |
|----------------|----------------|
| CAS No.: | 9011-05-6 |
| EC/EINECS No.: | Polymer Exempt |
| ENCS: | 7-576 |
| ECL: | KE-35175 |

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölnener Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

ASIA PACIFIC

Huber Engineered Materials
Zhang Ge Zhuang
Huangdao Sub-district
Qingdao, Shandong
266555 China

Web: www.martinswerk.de
www.hubermaterials.com

Email: info@martinswerk.com
hubermaterials@huber.com



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **PERGOPAK**® is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© April 2016 Martinswerk GmbH